

Mitsubishi Chemical Advanced Materials Ketron® 1000 IM Injection Molded Unfilled Polyetheretherketone (ASTM Product Data Sheet)

Mitsubishi Chemical Advanced Materials Ketron® 1000 IM Injection Molded Unfilled Polyetheretherketone (ASTM Product Data Sheet)			
Categories:	Polymer ; Thermoplastic ; Polyketone ; Polyetheretherketone (PEEK) ; Polyetheretherketone, PEEK, Unreinforced		
Material Notes:	<ul style="list-style-type: none"> • Excellent chemical resistance • Very low moisture absorption • Inherently good wear and abrasion resistance • Unaffected by continuous exposure to hot water or steam <p>Quadrant Engineering Plastic Products is now Mitsubishi Chemical Advanced Materials.</p>		
<hr/>			
Physical Properties	Metric	English	Comments
Specific Gravity	1.31 g/cc	1.31 g/cc	ASTM D792
Water Absorption	0.10 %	0.10 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	0.50 %	0.50 %	ASTM D 570(2)
<hr/>			
Mechanical	Metric	English	Comments

Properties			
Hardness, Rockwell M	107	107	ASTM D785
Hardness, Rockwell R	127	127	ASTM D785
Hardness, Shore D	88	88	ASTM D2240
Tensile Strength	110 MPa	16000 psi	ASTM D638
Elongation at Break	40 %	40 %	ASTM D638
Tensile Modulus	4.14 GPa	600 ksi	ASTM D638
Flexural Strength	159 MPa	23000 psi	ASTM D790
Flexural Modulus	4.14 GPa	600 ksi	ASTM D790
Compressive Strength	138 MPa	20000 psi	10% Def.; ASTM D695
Compressive Modulus	2.93 GPa	425 ksi	ASTM D695
Izod Impact, Notched	0.21 J/cm	0.40 ft-lb/in	ASTM D256 Type A
Coefficient of Friction, Dynamic	0.32	0.32	Dry vs. Steel; QTM55007
K (wear) Factor	755 x 10 ⁻⁸ mm ³ /N-M	375 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	QTM 55010
Limiting Pressure Velocity	0.298 MPa-m/sec	8500 psi-ft/min	4:1 safety factor; QTM 55007
Electrical Properties			
Surface Resistivity per Square	>= 1e+13 ohm	>= 1e+13 ohm	ASTM D257
Dielectric Constant	3.3 @Frequency 1e+6 Hz	3.3 @Frequency 1e+6 Hz	ASTM D150

Dielectric Strength	18.9 kV/mm	480 kV/in	Short Term; ASTM D149
Dissipation Factor	0.003 @Frequency 1e+6 Hz	0.003 @Frequency 1e+6 Hz	ASTM D150
Thermal Properties	Metric	English	Comments
CTE, linear	46.8 $\mu\text{m}/\text{m}\text{-}^\circ\text{C}$ @Temperature -40.0 - 150 $^\circ\text{C}$	26.0 $\mu\text{in}/\text{in}\text{-}^\circ\text{F}$ @Temperature -40.0 - 302 $^\circ\text{F}$	ASTM E831
Thermal Conductivity	0.252 W/m-K	1.75 BTU- in/hr-ft ² - $^\circ\text{F}$	ASTM E1530-11
Melting Point	340 $^\circ\text{C}$	644 $^\circ\text{F}$	Crystalline, Peak; ASTM D3418
Maximum Service Temperature, Air	249 $^\circ\text{C}$	480 $^\circ\text{F}$	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	160 $^\circ\text{C}$	320 $^\circ\text{F}$	ASTM D648
Flammability, UL94	V-0 @Thickness 3.17 mm	V-0 @Thickness 0.125 in	Estimated Rating

Some of the values displayed above may have been converted from their original units and/or rounded in order to display the information in a consistent format. Users requiring more precise data for scientific or engineering calculations can click on the property value to see the original value as well as raw conversions to equivalent units. We advise that you only use the original value or one of its raw conversions in your calculations to minimize rounding error. We also ask that you refer to MatWeb's disclaimer and terms of use regarding this

information. [Click here](#) to view all the property values for this datasheet as they were originally entered into MatWeb.